

# Vorpa MULTiset PLUS

Styrene free polyester pourable resin



products group



**MULTiset PLUS**  
content 5 kg.



**MULTiset PLUS**  
content 1 kg.

- Suitable for**
- concrete
  - natural stone
  - solid brick
  - marble



**+5°C/+25°C**

Store upright

**To fix**

- anchoring threaded steel bolts into solid surfaces, typically cementitious surfaces
- bedding-in coping stones, concrete units, steel, concrete or wooden posts
- repairs to large cracks in concrete surfaces requiring a self-levelling characteristic or difficult to reach areas
- traffic signs
- crash-noise barriers on the road
- bus shelters

product code and technical data

Code	Description	Content	Shelf life
1175	Multiset plus 5 kg	base and hardener	12 months in original closed cup
1174	Multiset plus 1 kg		

Mechanical characteristics	Standard	Average value [N/mm <sup>2</sup> ]
Tensile strength	ASTM D638	11,6
Tensile modulus	ASTM D638	5045
Compressive strength	ASTM D695	76
Compressive strength	EN 196-1	76
Flexural strength	ASTM D790	21
Flexural modulus	ASTM D790	1402


**Working and hardening times**

Base material temperature (C°)	5	10	20	25	30	35
Working time (min)	55	40	18	12	8	6
Loading time (min)	240	180	120	90	60	50

**Physical properties**

Unsaturated polyester resin colour grey  
Specific weight: 1,65 kg/l a 20°C VOC: 6,0 g/l

installation sequence



Clean the surfaces before the installation

Examples of applications

